



# Mill Test Certificate

**Bri-Steel Manufacturing Inc.**  
 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4  
 Tel: 001 (780) 469-6603  
 Fax: 001 (780) 469-6986  
 www.brichemsteel.com

Product: **Seamless Carbon Steel Pipe** Product Heat Number: **BSM-0066** Product Size: **NPS 20 STD** Production Date: **2011 Oct 21**

Production Method: **Hot Expansion** Product Heat Treatment: **As-rolled**

Product Standards: **ASTM/ASME A/SA106-2010 Grade B, A/SA53-2010 Grade B Type S, NACE MR0175-2009**

Product Markings: **.BRI-STEEL MFG NPS 20 STD ASTM/ASME A/SA106 GR B A/SA53 GR B HEAT BSM-0066 (PIPE # LENGTH MASS) NDE 800PSI NACE MR0175 2011/10 MADE IN CANADA.**

Product Details				Non-Destructive Testing											
Heat	Test Type	NPS	SCH	Pieces	Length	Mass	Geiger	Res. Mag.	Visual	OD	UT	UT	ET	HydroTest	End
BSM-0066	Heat	20	STD	3	DRL	9424 LB	µR/hr	Gauss	Insp.	Pass	Pass	ASTM E213	ASTM E309	800 psi/5s	Condition
							<5	<20	Pass	Pass	---	Pass	Pass	Pass	37.5° Bevel

		Chemical Analysis (wt%)																
Heat	Test Type	Steelmaking Method		C	Mn	P	S	Si	Cr	Cu	Mo	Ni	V	Ti	Nb	B	CE	CE
BSM-0066	Heat	Blast Furnace; EAF; Ladle Refining; Vacuum Degas		0.21	0.88	0.016	0.009	0.23	0.03	0.11	0.02	0.03	0.003	0.001	0.001	0.0002	0.38	0.38

Mechanical Properties									
Heat	Test Type	Microstructure	Hardness	Flattening Test	Tension Test	Yield (Rt0.5)	Yield (Rp0.2)	Tensile (Rm)	Elongation (A)
BSM-0066	Heat	Ferrite & Pearlite	HRBW	Pass	Transverse; 50mm GL; 38mm x WT	psi	psi	psi	%
			78			46,600	46,600	76,000	42

**Additional Details:**

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements.
- ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service, and NACE MR0103-2010 Section 2.1.

Mill Test Certificate approved by:

2011 Nov 2

Kenton Dechant, P.Eng.  
 Manager of Quality and R&D