

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986

www.brichemsteel.com

Product Heat Number: BSM-0109 Product Size: NPS 18 STD Production Date: 2011 Nov 21

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Seamless Carbon Steel Pipe

Product Standards: ASTM/ASME A/SA106-2010 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

**Product Markings:** .BRI-STEEL MFG NPS 18 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0109 (PIPE # LENGTH MASS) NDE 1030PSI NACE MR0175 2011/11 MADE IN CANADA.

|      | BSM-0109    | Heat        |           |                |
|------|-------------|-------------|-----------|----------------|
|      |             |             |           |                |
|      | Heat        | Test Type   |           |                |
|      | 18          | NPS         |           | P              |
| 2000 | STD         | SCH         |           | Product Detail |
|      | ω           | Pieces      |           | ils            |
|      | DRL         | Length      |           |                |
|      | 8399 LB     | Mass        |           |                |
|      | G           | μR/hr       | Geiger    |                |
|      | <20         | Gauss       | Res, Mag. |                |
|      | Pass        | Insp.       | Visual    |                |
|      | Pass        | OD          |           | Non-L          |
|      | Pass        | WT          | IN        | Destructive 1  |
|      |             | ASTM E213   | TU        | esting         |
|      | Pass        | ASTM E309   | ET        |                |
|      | Pass        | 1030 psi/5s | HydroTest |                |
|      | 37.5° Bevel | Condition   | End       |                |

| BSM-0109               | Heat                      |    |              |
|------------------------|---------------------------|----|--------------|
| 109                    | ╁                         |    |              |
| Heat                   | Test Type                 |    |              |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle |    |              |
| 0.20                   | 0                         |    |              |
| 0.87                   | Mn                        |    |              |
| 0.015                  | P                         |    |              |
| 0.010                  | S                         |    | Chemical A   |
| 0.22                   | Si                        |    | Analysis (wt |
| 0.03                   | ٠                         |    | (wt%)        |
| 0.11                   | Cn                        |    |              |
| 0.01                   | Mo                        |    |              |
| 0.04                   | Z.                        |    |              |
| 0.003                  | <                         |    |              |
| 0.001                  | Ti                        |    |              |
| 0.001                  | Nb                        |    |              |
| 0.0001                 | В                         |    |              |
| 0.36                   | (WII)                     | CE |              |
| 0.37                   | (CSA)                     | Œ  |              |

| Longitudinal | BSM-0109 Heat Ferrite & Pearlite 80 Pass Transverse | Heat Test Type Microstructure HRBW Flattening Test 50mm GL; 38mm x WT | Hardness Tension Test | viecnanical Properties |
|--------------|---|---|-----------------------|------------------------|
|              | 80  | HRBW  | Hardness              |                        |
|              | Pass  | Flattening Test   |                       | iviecnal               |
| Longitudinal | Transverse  |   | Tension Test          | nical Properties       |
| 50,500       | 52,500  | psi   | Yield (Rt0.5)         |                        |
| 51,500       | 52,500  | psi   | Yield (Rp0.2)         |                        |
| 74,500       | 75,000  | psi   | Tensile (Rm)          |                        |
| 0.68         | 0.70  | (Rt0.5/Rm)  | Τ/Υ                   |                        |
| 40           | 38  | %   | Elongation (A)        |                        |

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1.  $\checkmark~$  This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

✓ No weld repairs have been performed on this product. This product has no mercury contamination. ✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

ZOILDEC13

Manager of Quality and R&D