

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Mill Test Certificate

Product Heat Number:

BSM-0121

Product Size:

NPS 18 STD

Production Date:

2011 Nov 29

Product:

Seamless Carbon Steel Pipe

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2010 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 18 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0121 (PIPE # LENGTH MASS) NDE 1030PSI NACE MR0175 2011/11 MADE IN CANADA.

| 37.5° Bevel | Pass | Pass | 1 | Pass | Pass | Pass | <20 | S | 2817 LB | DRL | Н | STD | 18 | Heat | BSM-0121 |
|-------------|-------------|-----------|-----------|----------------|-------|--------|----------|--------|---------|--------|--------|----------------|-----|-----------|----------|
| Condition | 1030 psi/5s | ASTM E309 | ASTM E213 | WT | OD | Insp. | Gauss | μR/hr | Mass | Length | Pieces | SCH | NPS | Test Type | Heat |
| End | HydroTest | ET | UT | T | | Visual | Res.Mag. | Geiger | | | 8 | | | | : |
| | | | Testing | -Destructive 1 | Non-D | | | | | | ls | Product Detail | Pr | | |

| BS | Τ | | Γ |
|------------------------|---------------------------|--------------------|------------|
| BSM-0121 | - | | |
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.20 | 0 | | |
| 0.87 | Mn | | |
| 0.009 | P | | |
| 0.012 | S | | Chemica |
| 0.22 | Si | | l Analysis |
| 0.03 | Ç, | | (wt%) |
| 0.10 | Cu | | |
| 0.01 | Mo | | |
| 0.03 | <u>N</u> | | |
| 0.002 | < | | |
| 0.001 | T: | | |
| 0.001 | Nb | | |
| 0.0002 | В | | |
| 0.36 | (IIW) | CE | |
| 0.37 | (CSA) | Œ | |

| | BSM-0121 | Heat | | |
|--------------|--------------------|----------------------|----------------|-----------------------|
| | Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 78 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechar |
| Longitudinal | Transverse | t 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 49,700 | 46,200 | psi | Yield (Rt0.5) | |
| 49,800 | 45,800 | psi | Yield (Rp0.2) | |
| 75,500 | 75,500 | psi | Tensile (Rm) | |
| 0.66 | 0.61 | (Rt0.5/Rm) | Τ/Υ | |
| 38 | 34 | % | Elongation (A) | |

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2011 Dec 13