

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0152

Product Size:

NPS 30 STD

Production Date:

2011 Dec 20

Production Method: **Hot Expansion** 

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2010 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 30 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0152 (PIPE # LENGTH MASS) NDE 630PSI NACE MR0175 2011/11 MADE IN CANADA.

	BSM-0152	Heat		
	Heat	Test Type		
	30	NPS		P
	STD	SCH		Product Detail
	œ	Pieces		ls
	DRL	Length		
	118.6	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
and the second second second second	Pass	OD		Non-I
	Pass	WT	TU	Non-Destructive 1
0.00		ASTM E213	TU	ve Testing
	Pass	ASTM E309	ET	
	Pass	ASTM E213 ASTM E309 630 psi/5s   Condition	HydroTest	
	37.5° Bevel	Condition	End	

BSM-0152	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.22	С		
0.90	Mn		
0.015	Ъ		
0.006	S	- 146	Chemical Ana
0.24	Si		l Analysis (wt%)
0.05	Ω.		(wt%)
0.06	Cu		
0.01	Mo		
0.03	Z.		
0.005	٧		
0.002	T		
0.001	Nb		
0.0001	В		
0.39	(IIW)	CE	
0.40	(CSA)	CE	

		BSM-0	Heat		
		BSM-0152 Heat		_	
		Heat	Test Type		
		Ferrite & Pearlite	Microstructure		
		75	HRBW	Hardness	
		Pass	Flattening Test		Mechar
	Longitudinal	Transverse	50mm GL; 38mm x WT	Tension Test	Mechanical Properties
Section of the sectio	44,200	42,100	psi	Yield (Rt0.5)	
	43,800	41,600	psi	Yield (Rp0.2)	
- AND	70,000	70,500	psi	Tensile (Rm)	
200	0.63	0.60	(Rt0.5/Rm)	1/4	
	43	44	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

As per client requirements, diameter does not exceed 30.250 inches.

Mill Test Certificate approved by:

2012 Feb 3

Manager of Quality and R&D Kenton Dechant, P.Eng.