

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Seamless Carbon Steel Pipe Product Heat Number: BSM-0157 Product Size: NPS 30 STD

Production Date: 2011 Dec 22

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product:

Product Standards: ASTM/ASME A/SA106-2010 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 30 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0157 (PIPE # LENGTH MASS) NDE 630PSI NACE MR0175 2011/11 MADE IN CANADA.

		Т	_	_		_	
	BSM-0157	חפמנ	E 0 2 +		10000		
	Heat	lest Type	Toct Time				
	30	NPS	200			-	
	STD	SCH	0			Product Detail	
	ω	Pieces	7			S	
	DRL	Lengin					
	118.6	ID/IT	- 6	Mass			
	\$	μκ/hr)	Geiger			
	<20	Gauss)	Res.Mag.			
	Pass	Insp.		Visual			
	Pass	OD	1			Non-D	
	Pass	WT		T		estructive T	
-		ASTM E213		T		esting	
	Pass	ASTM E309		듸			
	Pass	E309 630 psi/5s Co		HydroTest			
	37.5° Bevel	Condition		End			

BSM-0157	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.20	C		
0.86	Mn		
0.014	P		
0.007	S		Chemical
0.24	Si		l Analysis
0.05	Ů,		; (wt%)
0.07	Cu		
0.01	Mo		8
0.02	Z.		
0.004	<		
0.001	#		
0.001	Nb		
0.0002	В		
0.36	(IIW)	Œ	
0.37	(CSA)	Œ	

		_	_	_
	BSM-0157 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
44,100	48,000	psi	Yield (Rt0.5)	
44,100	48,000	psi	Yield (Rp0.2)	
69,000	71,000	psi	Tensile (Rm)	
0.64	0.68	(Rt0.5/Rm)	Υ/Τ	
40	46	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements. ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

 \prime This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. \checkmark No weld repairs have been performed on this product. This product has no mercury contamination.

As per client requirements, diameter does not exceed 30.250 inches.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

2012 Feb 3

Manager of Quality and R&D