

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Production Date: 2012 Jan 9

Seamless Carbon Steel Pipe

Product:

Production Method:

Hot Expansion

Product Heat Number:

BSM-0170

Product Size:

NPS 16 STD

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2010 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings:

| BSM-0170 | Heat | | |
|-------------|-------------|-----------|-----------------|
| Heat | Test Type | | |
| 16 | NPS | | P |
| STD | SCH | | Product Detail: |
| 1 | Pieces | | ls |
| DRL | Length | | |
| 82.77* | lb/ft | Mass | |
| <5 | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | Insp. | Visual | |
| Pass | OD | 0.00 | Non-D |
| Pass | TW | TU | Destructive 1 |
| | ASTM E213 | TU | esting |
| Pass | ASTM E309 | ET | |
| Pass | 1490 psi/5s | HydroTest | |
| 37.5° Bevel | Condition | End | |

.BRI-STEEL MFG NPS 16 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0170 (PIPE # LENGTH MASS) NDE 1490PSI NACE MR0175 2011/11 MADE IN CANADA.

| BSM-0170 | Heat | | |
|------------------------|---------------------------|--------------------|------------|
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.20 | С | | |
| 0.88 | Mn | | |
| 0.012 | Р | | |
| 0.015 | S | | Chemica |
| 0.25 | Si | | l Analysis |
| 0.06 | Cr | | (wt%) |
| 0.11 | Cu | | |
| 0.03 | Mo | | |
| 0.05 | Z. | | |
| 0.003 | < | | |
| 0.001 | = | | |
| 0.001 | Nb | | |
| 0.0002 | В | | |
| 0.38 | (IIW) | Œ | |
| 0.38 | (CSA) | Ж | |

| | BSM-0170 | Heat | | |
|--------------|--------------------|------------------------------------|----------------|-----------------------|
| | Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 77 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechan |
| Longitudinal | Transverse | Flattening Test 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 46,300 | 51,500 | psi | Yield (Rt0.5) | |
| 45,900 | 50,500 | psi | Yield (Rp0.2) | |
| 74,000 | 74,500 | psi | Tensile (Rm) | |
| 0.63 | 0.69 | (Rt0.5/Rm) | Τ/Υ | |
| 46 | 39 | % | Elongation (A) | |

Additional Details:

- Inc. in accordance with ASTM/ASME A/SA106-2010, A/SA53-2010 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing results meet the corresponding requirements.
- Service, and NACE MR0103-2010 Section 2.1. No weld repairs have been performed on this product. This product has no mercury contamination.

 \checkmark This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

- This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- *This product was recertified as NPS 16 STD from NPS 16 XS due to the presence of thin regions in the pipe wall thickness.

Mill Test Certificate approved by:

2012Feb15

Manager of Quality and R&D Kenton Dechant, P.Eng.