

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0237

Product Size:

NPS 24 TRUE40

Production Date: February 29, 2012

Production Method: **Hot Expansion** Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 TRUE40 ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0237 (PIPE # LENGTH MASS) NDE 740PSI NACE MR0175 2012/02 MADE IN CANADA.

| | <u></u> | Т | _ | Т |
|------|-------------|------------|-----------|----------------|
| | BSM-0237 | Heat | | |
| | Heat | Test Type | | |
| | 24 | NPS | | - |
| W200 | TRUE40 | SCH | | Product Detail |
| | 3 | Pieces | | S |
| | DRL | Length | | |
| | 171.20 | lb/ft | Mass | |
| | ŝ | μR/hr | Geiger | |
| | <20 | Gauss | Res.Mag. | |
| | Pass | Insp. | Visual | |
| | Pass | OD | | Non-E |
| | Pass | WT | TU | Destructive ' |
| | | ASTM E213 | TU | Testing |
| | Pass | ASTM E309 | ET | |
| | Pass | 740 psi/5s | HydroTest | |
| | 37.5° Bevel | Condition | End | |

| BSM-0237 | Heat | | |
|------------------------|---------------------------|--------------------|------------|
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.19 | С | | |
| 0.86 | Mn | | |
| 0.010 | P | | |
| 0.006 | S | | Chemical , |
| 0.24 | Si | | l Analysis |
| 0.04 | ਨ | | (wt%) |
| 0.11 | Cu | | |
| 0.01 | Mo | | |
| 0.03 | Z. | | |
| 0.003 | < | | |
| 0.001 | Ti | | |
| 0.001 | Nb | | |
| 0.0001 | В | | |
| 0.35 | (IW) | CE | |
| 0.36 | (CSA) | Э | |

| | | [| Т | | Т |
|----|---------------|--------------------|------------------------------------|----------------|-----------------------|
| | | BSM-0237 | Heat | | |
| | BSM-0237 Heat | | Test Type | | |
| | | Ferrite & Pearlite | Microstructure | | |
| | | 75 | HRBW | Hardness | |
| 70 | | Pass | Flattening Test | | Mechan |
| | Longitudinal | Transverse | Flattening Test 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| | 43,500 | 43,500 | psi | Yield (Rt0.5) | |
| | 43,300 | 42,700 | psi | Yield (Rp0.2) | |
| | 71,000 | 71,000 | psi | Tensile (Rm) | |
| | 0.61 | 0.61 | (Rt0.5/Rm) | Τ/γ | |
| | 52 | 52 | % | Elongation (A) | |

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements. We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

 $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. \checkmark No weld repairs have been performed on this product. This product has no mercury contamination

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2012 Mar 14

Manager of Quality and R&D