

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 124 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0240

Product Size:

NPS 24 STD

Production Date: March 1, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0240 (PIPE # LENGTH MASS) NDE 740PSI NACE MR0175 2012/03 MADE IN CANADA.

| <u></u> | Т | | Т |
|-------------|------------|-----------|----------------|
| BSM-0240 | Heat | | |
| Heat | Test Type | | |
| 24 | NPS | | P |
| STD | SCH | | Product Detail |
| 1 | Pieces | | ils |
| DRL | Length | | |
| 94.62 | lb/ft | Mass | |
| S | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | Insp. | Visual | |
| Pass | OD | | Non-E |
| Pass | TW | TU | Destructive T |
| | ASTM E213 | TU | e Testing |
| Pass | ASTM E309 | ET | |
| Pass | 740 psi/5s | HydroTest | |
| 37.5° Bevel | Condition | End | |
| | | | |

| BSM-0240 | Heat | | |
|------------------------|---------------------------|--------------------|------------|
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.21 | C | | |
| 0.90 | Mn | | |
| 0.012 | P | | |
| 0.011 | S | | Chemica |
| 0.24 | Si | | l Analysis |
| 0.03 | Ç | | (wt%) |
| 0.10 | Cu | | |
| 0.01 | Mo | | |
| 0.03 | Z: | | |
| 0.004 | < | | |
| 0.001 | Ti | | |
| 0.002 | Nb | | |
| 0.0001 | В | | |
| 0.38 | (WII) | æ | |
| 0.39 | (CSA) | æ | |

| | BSM-0240 Heat | Heat | | |
|--------------|--------------------|------------------------------------|----------------|-----------------------|
| | Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 79 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechar |
| Longitudinal | Transverse | Flattening Test 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 47,900 | 47,000 | psi | Yield (Rt0.5) | |
| 47,900 | 45,100 | psi | Yield (Rp0.2) | |
| 73,500 | 81,000 | psi | Tensile (Rm) | |
| 0.65 | 0.58 | (Rt0.5/Rm) | Τ/Υ | |
| 43 | 44 | % | Elongation (A) | |

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the 🗸 We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. \checkmark This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

 $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1. No weld repairs have been performed on this product. This product has no mercury contamination

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

2012 Mar 19.

Manager of Quality and R&D