

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0283

Product Size:

NPS 16 STD

Production Date: April 5, 2012

Production Method: **Hot Expansion**

Product Heat Treatment:

As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 16 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0283 (PIPE # LENGTH MASS) 62.58lb/ft NDE 1140PSI NACE MR0175 2012/04 MADE IN CANADA.

BSM-0283	Heat		
33 Heat	1		
16			
STD	SCH		Product Detail
17	Pieces		ails
DRL	Length		
62.58	lb/ft	Mass	
ŝ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	insp.	Visual	
Pass	00		Non-I
Pass	WT	TU	Destructive T
1	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
Pass	1140 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

BSM-0283	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.21	С		
0.88	Mn		
0.011	Р		
0.011 0.018	S		Chemica
0.22	Si		Analysis
0.05	Cr		(wt%)
0.09	Cn		
0.03	Mo		
0.05	Z:		
0.003	<		
0.001	Ti		
0.002	Nb	U0070	
0.0002	В		
0.38	(IIW)	Œ	
0.39	(CSA)	Œ	

	E	Т		
	BSM-0283 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	50mm GL; 38mm x WT	Tension Test	Mechanical Properties
44,600	46,000	psi	Yield (Rt0.5)	
44,400	45,800	psi	Yield (Rp0.2)	
74,000	74,000	psi	Tensile (Rm)	
0.60	0.62	(Rt0.5/Rm)	Τ/Υ	×
38	40	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the $\checkmark~$ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2012 Apr 16