

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0295

Product Size: NPS 20 STD

Production Date:

April 20, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 20 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0295 (PIPE # LENGTH MASS) 78.6Ib/ft NH NDE NACE MR0175 2012/04 MADE IN CANADA.

	[w	Г		Т
	BSM-0295	Heat		
	Heat	Test Type		
	20	NPS		7
	STD	SCH		roduct Detail:
	1	Pieces		lis
	DRL	Length		
	78.60	lb/ft	Mass	
	ŝ	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-E
	Pass	WT	T	Destructive 1
		ASTM E213	TU	e Testing
	Pass	ASTM E309	ET	
The second secon	*	M E309 910 psi/5s	HydroTest	
	37.5° Bevel	Condition	End	

		_	_	_
	BSM-0295	Heat	:	
	Heat	Test Type	i	
	Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	I iii	
	0.20	0		
	0.85	Mn		
	0.014	P		
	0.010	S		Chemica
	0.22	Si		Analysis (wt%)
	0.03	ç		(wt%)
	0.11	Cr		
	0.03	Mo		
	0.03	N.		
	0.002	٧		
	0.001	#		
	0.001	Nb		
	0.0002	В		
	0.36	(WII)	CE	
	0.37	(CSA)	Æ	
ľ				_

	BSM-02	Heat		
	BSM-0295 Heat	t Test Type		
	at	Уре		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
45,100	43,900	psi	Yield (Rt0.5)	
44,900	43,000	psi	Yield (Rp0.2)	
69,500	75,000	psi	Tensile (Rm)	
0.65	0.59	(Rt0.5/Rm)	۲/۲	
39	37	%	Elongation (A)	

Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour No weld repairs have been performed on this product. This product has no mercury contamination
- *Note that this pipe was too short to be able to perform the hydrotest. This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

2012 June 13

Manager of Quality and R&D Kenton Dechant, P.Eng.