

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0303 Product Size:

NPS 20 STD

Production Date: April 25, 2012

Production Method: **Hot Expansion**

Product Standards:

Product Heat Treatment: As-rolled

ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 20 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0303 (PIPE # LENGTH MASS) 78.61b/ft NDE 910PSI NACE MR0175 2012/04 MADE IN CANADA.

BSM-0303	Heat	37	
Heat	Test Type		
20	NPS		P
STD	SCH		Product Detail
7	Pieces		ils
DRL	Length		
78.60	lb/ft	Mass	
\$	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-[
Pass	WT	디	Destructive 1
	ASTM E213	TU	esting
Pass	ASTM E309	ET	
Pass	910 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

BSM-0303	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.22	C		
0.56	ĭ		
0.013	P		
0.007	S		Chemical Analysis (wt%)
0.24	Si		Analysis
0.03	ς,		(wt%)
0.02	Cu		
0.01	Mo		
0.01	<u>Z</u> .		
0.002	<		
0.002	=		
0.001	Nb		
0.0001	В		
0.32	(WII)	CE	
0.33	(CSA)	CE	

	BSM-0303 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	73	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	50mm GL; 38mm x WT	Tension Test	Mechanical Properties
43,500	41,400	psi	Yield (Rt0.5)	11
43,700	40,300	psi	Yield (Rp0.2)	
68,500	71,500	psi	Tensile (Rm)	
0.64	0.58	(Rt0.5/Rm)	Υ/Τ	
44	44	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

Manager of Quality and R&D