

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

> Product Heat Number: BSM-0309

Product Size:

NPS 20 TRUE40

Production Date:

April 30, 2012

Production Method: **Hot Expansion**

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 20 TRUE40 ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0309 (PIPE # LENGTH MASS) 122.91b/ft NDE 1370PSI NACE MR0175 2012/04 MADE IN CANADA.

	В	Т		Т
	BSM-0309	Heat		
	Heat	Test Type		
	20	NPS		_
	TRUE40	SCH		Product Detail
	4	Pieces		S
	DRL	Length	9	
	122.90	lb/ft	Mass	
	ŝ	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-D
	Pass	WT	TU	estructive T
	2	ASTM E213	TU	esting
	Pass	ASTM E309	ET	
	Pass	1370 psi/5s	HydroTest	
	Plain End	Condition	End	
- 1				

	BS	Γ	_	Τ
	BSM-0309	Heat		
	Heat	Test Type		
	Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
	0.19	0		
	0.87	Mn		
	0.010	Р		
	0.008	S		Chemical
	0.23	Si		l Analysis (wt%)
	0.05	Ç,		(wt%)
	0.07	Cn		
	0.01	Mo		
100000000000000000000000000000000000000	0.03	N.		
	0.010	٧		
	0.001	Ti		
	0.001	Nb		
	0.0001	В		
S = 5000 dc	0.36	(IIW)	æ	
	0.36	(CSA)	CE	

		_		_
	BSM-0309	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	78	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
44,300	47,300	psi	Yield (Rt0.5)	
44,200	45,500	psi	Yield (Rp0.2)	
72,500	73,000	psi	Tensile (Rm)	
 0.61	0.65	(Rt0.5/Rm)	Τ/Υ	
47	44	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

2012/May

Manager of Quality and R&D