

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603 Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0317

Product Size:

Mill Test Certificate

e: NPS 24 STD

Pro

Production Date: May 7, 2012

Production Method: Hot Expansion

Hot Expansion Product Heat Tre

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0317 (PIPE # LENGTH MASS) 94.621b/ft NDE 740PSI NACE MR0175 2012/05 MADE IN CANADA.

| | _ | | Т |
|-------------|------------|-----------|----------------|
| BSM-0317 | Heat | | |
| Heat | Test Type | | |
| 24 | NPS | | P |
| STD | SCH | | Product Detail |
| 1 | Pieces | | ls |
| DRL | Length | | |
| 94.62 | lb/ft | Mass | |
| G | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | Insp. | Visual | |
| Pass | OD | | Non-E |
| Pass | WT | TU | estructive T |
| | ASTM E213 | TU | esting |
| Pass | ASTM E309 | ΕT | |
| Pass | 740 psi/5s | HydroTest | |
| 37.5° Bevel | Condition | End | |
| | | | |

| BSM-0317 | Heat | | |
|------------------------|---------------------------|--------------------|------------|
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.20 | С | 200 | |
| 0.89 | Mn | | |
| 0.012 | P | | |
| 0.008 | S | | Chemica |
| 0.27 | Si | | l Analysis |
| 0.03 | ር | | (wt%) |
| 0.11 | Cu | | |
| 0.03 | Mo | | |
| 0.04 | Z. | | |
| 0.002 | < | | |
| 0.001 | ∄ | | |
| 0.001 | Nb | | |
| 0.0001 | В | | |
| 0.37 | (IIW) | Œ | |
| 0.38 | (CSA) | Œ | |

| | BSM-031; | Heat | | |
|--------------|--------------------|------------------------------------|----------------|-----------------------|
| | BSM-0317 Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 78 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechan |
| Longitudinal | Transverse | Flattening Test 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 48,400 | 41,900 | psi | Yield (Rt0.5) | |
| 48,400 | 40,700 | psi | Yield (Rp0.2) | |
| 74,000 | 74,500 | psi | Tensile (Rm) | |
| 0.65 | 0.56 | (Rt0.5/Rm) | 1/4 | |
| 39 | 44 | % | Elongation (A) | |

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements. ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

Service, and NACE MR0103-2010 Section 2.1.

No weld repairs have been performed on this product. This product has no mercury contamination

✓ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.
Manager of Quality and R&D