

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0320

Product Size:

NPS 24 STD

Production Date: May 9, 2012

Production Method: Hot Expansion Product Heat Treatment: As-rolled

Product Standards:

ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0320 (PIPE # LENGTH MASS) 94.621b/ft NDE 740PSI NACE MR0175 2012/05 MADE IN CANADA.

BSM-0320	Heat	=	
20 Heat	1	- - -	
24			
STD	SCH		Product Det
4	Pieces		ails
DRL	Length		
94.62	lb/ft	Mass	
ŝ	µR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	T	estructive
-	ASTM E213	u	Testing
Pass	ASTM E309	曰	
Pass*	740 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

10000	BSM-0320		прац				
	U Heat		lest Type	1			
	Retining; Vacuum Degas		Blast Furnace; EAF; Ladle		Steelmaking Method		
	0.21		<u> </u>				
	0.87		S <sub>n</sub>				
	0.014   0.007		ъ				
	0.007		S			Chemical	
	0.25		S			ical Analysis (wt%)	
	0.04		ڻ ر			(wt%)	
	0.12		5				
	0.04		ŏ.				
	0.04		Z.				
	0.003		<				
	0.001		=!				
2000	0.001		2				
20000	0 0001	-	B				
0.00	8£ U			0.1	CF		
0.00	0 3 q	1000	(CSA)	()	CF		

	BSM-0320 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
47,100	42,700	psi	Yield (Rt0.5)	
47,200	41,700	psi	Yield (Rp0.2)	
76,500	76,000	psi	Tensile (Rm)	
0.62	0.56	(Rt0.5/Rm)	۲/۲	
40	41	%	Elongation (A)	

## Additional Details:

- results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. No weld repairs have been performed on this product. This product has no mercury contamination

This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

\*Pipe 003 was too short to perform the hydrotest.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2012 May 24

Manager of Quality and R&D