

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0322

Product Size:

NPS 24 STD

Production Date: May 10, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0322 (PIPE # LENGTH MASS) 94.621b/ft NDE 740PSI NACE MR0175 2012/05 MADE IN CANADA.

BSN	L		Γ
BSM-0322	Heat		
Heat	Test Type		
24	NPS		P
STD	SCH		Product Detai
2	Pieces		ls
DRL	Length		
94.62	lb/ft	Mass	
Ġ	μR/hr	Geiger	i
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	T	Destructive T
	ASTM E213	TU	esting
Pass	ASTM E309	ET	
Pass*	740 psi/5s	HydroTest	
37.5° Bevel	Condition	End	

BSM-0322	Heat	1	
Heat	=	i	
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.19	0		
0.90	Mn		
0.015	P		
0.015   0.011	S		Chemica
0.24	Si		l Analysis
0.03	ç,	20.00	(wt%)
0.12	C		
0.03	Mo		
0.04	Z		
0.003	<		
0.001	=		
0.002	Nb		
0.0001	В		
0.36	(IIW)	CE	
0.37	(CSA)	Œ	

	BSM-0322 Heat	Heat	K N	
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
49,300	44,100	psi	Yield (Rt0.5)	
49,300	43,000	psi	Yield (Rp0.2)	
74,500	74,000	psi	Tensile (Rm)	
0.66	0.60	(Rt0.5/Rm)	T/Y	20
39	40	%	Elongation (A)	

## Additional Details:

- Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements.  $\checkmark~$  We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing
- Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour
- No weld repairs have been performed on this product. This product has no mercury contamination
- \*Pipe 001 was too short to perform the hydrotest. This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 42 Kay 2102

Manager of Quality and R&D