

## Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

> Product Heat Number: BSM-0327

Product Size:

NPS 24 STD

Production Date: May 15, 2012

Production Method: **Hot Expansion** 

Product Standards:

Product Heat Treatment: As-rolled

ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2010 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0327 (PIPE # LENGTH MASS) 94.621b/ft NDE 740PSI NACE MR0175 2012/05 MADE IN CANADA.

	BSM-0327	Heat		
	Heat	Test Type		
	24	NPS		P
	STD	SCH		Product Detail
	9	Pieces		is
	DRL	Length	9	
2000	94.62	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass	OD		Non-D
	Pass	WT	TU	estructive T
		ASTM E213 ASTI	TU	Testing
	Pass	ASTM E309	ET	
	Pass	740 psi/5s	HydroTest	
	37.5° Bevel	Condition	End	

BSM-0327	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.20	0		
0.89	Mn		
0.013	P		
0.013	S		Chemical A
0.20	Si		l Analysis (wt%)
0.03	Cr		(wt%)
0.13	Cu		
0.02	Mo		
0.04	<u>Z.</u>		
0.003	٧		
100.0	П		
100.0	Nb		
0.0002	В		
0.37	(IIW)	Œ	
0.38	(CSA)	Œ	

	BSM-0327 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
45,600	42,900	psi	Yield (Rt0.5)	
42,900	41,300	psi	Yield (Rp0.2)	
74,500	73,500	psi	Tensile (Rm)	
0.61	0.58	(Rt0.5/Rm)	T/Y	
41	39	%	Elongation (A)	

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2010 and the purchase order requirements, and that the results meet the corresponding requirements.

 $\checkmark$  This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

Service, and NACE MR0103-2010 Section 2.1. No weld repairs have been performed on this product. This product has no mercury contamination

 $\checkmark~$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.