

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Production Method:

Product Heat Number: BSM-0349

Product Size:

Mill Test Certificate

NPS 16 STD

Production Date:

May 29, 2012

Hot Expansion Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2012 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 16 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0349 (PIPE # LENGTH MASS) 62.581b/ft NDE 1140PSI NACE MR0175 2012/05 MADE IN CANADA.

BSI			Γ
BSM-0349	Heat		
Heat	Test Type		
16	NPS		P
STD	SCH		Product Detail
6	Pieces		ls
DRL	Length		
62.58	lb/ft	Mass	
Ġ	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	99		Non-I
Pass	WT	TU	Destructive '
-	ASTM E213	TU	esting
Pass	ASTM E309	ET	
Pass	1140 psi/5s	HydroTest	
37.5° Bevel	i/5s Condition	End	

CHCO-IAICG	DCM	Неат			
040	00/00				
near		lest lype		000000	
neiming, vacuum Degas		Blast Furnace; EAF; Ladle	Steermaking Method	Ct-clustin Nath-1	
0.22	3	0			
0.90	8	S			
0.010	200	Р			
0.004	000	S			Chemical
0.22	2	Si			Analysis (wt%)
0.03	2	Ç			(wt%)
80.0	200	5			
0.02	0	ŏ o			
0.03		Z			
0.002		<			
0.002		_!			
0.002		N _D			
0.0003		В			
0.39	-	<u>=</u>	Œ		
0.40		(CSA)	Œ		

			Т		Т
		BSM-0349 Heat	Heat		
		Heat	Test Type		
		Ferrite & Pearlite	Microstructure		
		78	HRBW	Hardness	
		Pass	Flattening Test		Mechan
	Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
	48,900	46,600	psi	Yield (Rt0.5)	
	48,700	45,000	psi	Yield (Rp0.2)	
500	76,500	75,500	psi	Tensile (Rm)	
A	0.64	0.62	(Rt0.5/Rm)	1/7	
100000000000000000000000000000000000000	36	37	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

 \prime No weld repairs have been performed on this product. This product has no mercury contamination

 $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

5012 June 13

Manager of Quality and R&D Kenton Dechant, P.Eng.