

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product Size: NPS 20 TRUE80 Production Date: June 18, 2012

BSM-0369

Production Method: Product Heat Number:

Product:

Seamless Carbon Steel Pipe

Hot Expansion Product Heat Treatment: As-rolled

ASTM/ASME A/SA106-2011 Grade B, A/SA53-2012 Grade B Type S, NACE MR0175-2009

Product Standards:

Product Markings: .BRI-STEEL MFG NPS 20 TRUE80 ASTM/ASME A/SA106 GR B A/SA53 GR B HEAT BSM-0369 (PIPE # LENGTH MASS) 208.91b/ft NDE 1000PSI NACE MR0175 2012/06 MADE IN CANADA.

	_		_
BSM-0369	Heat		
Heat	Test Type		
20	NPS		P
TRUE80	SCH		Product Detail
1	Pieces		ls
DRL	Length		
208.90	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
 Pass	OD		Non-D
Pass	TW	TU	estructive T
	ASTM E213	TU	esting
Pass	ASTM E309	ET	
Pass	1000 psi/5s	HydroTest	
Plain End	Condition	End	
_			_

BSM-0369	Heat		Γ
0369			
Heat	Test Type	_	
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.16	C		
1.02	Mn		
0.022	P		
0.007	S		Chemical
0.25	Si		Analysis (wt%
0.05	Ç		(wt%)
0.06	Cu		
0.01	Mo		
0.02	Z.		
0.005	<		
0.003	Ti		
0.002	Nb		
0.0002	В		
0.35	(IIW)	Œ	
0.34	(CSA)	CE	

			_	_	_
	BSM-0369 Heat	Heat			
	Heat	Test Type			
	Ferrite & Pearlite	Microstructure			
	69	HRBW		Hardness	
	Pass	Flattening Test			Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	ו כווסוטוו ובטנ	Tension Test	Mechanical Properties
45,800	44,900	psi.	ווכום (וזנט.ט)	Viald (R+0 5)	
42,600	42,200	psi.	ווכום (ווסט.ב)	Viold (Bn0 3)	
64,500	65,000	psi.	Tensile (mil)	Tancila (Pm)	
0.71	0.69	(Rt0.5/Rm)	1/1	V/T	
60	58	%	CIOIBacion (A)	Elopation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

 $\checkmark~$ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination

Service, and NACE MR0103-2010 Section 2.1.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2012 June 27

Manager of Quality and R&D