

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0378

Product Size:

NPS 18 XS

Production Date:

June 25, 2012

Production Method: Hot Expansion

Product Heat Treatment:

As-rolled

Product Markings: Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2012 Grade B Type S, NACE MR0175-2009 .BRI-STEEL MFG NPS 18 XS ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0378 (PIPE # LENGTH MASS) 93.45Ib/ft NDE 1370PSI NACE MR0175 2012/06 MADE IN CANADA.

| BSM-0378 | Heat | | |
|-------------|---------------------------------|-----------|----------------|
| | L | | |
| Heat | Test Type | | |
| 18 | NPS | | ₽ |
| XS | SCH | | Product Detail |
| 7 | Pieces | | S |
| DRL | Length | | |
| 93.45 | lb/ft | Mass | |
| ራ | μR/hr | Geiger | |
| <20 | Gauss | Res.Mag. | |
| Pass | insp. | Visual | |
| Pass | OD. | | Non-D |
| Pass | WT | UΤ | estructive T |
| | ASTM E213 | Τ'n | · Testing |
| Pass | ASTM E309 | ET | |
| Pass | STM E309 1370 psi/5s Conditio | HydroTest | |
| 37.5° Bevel | Condition | End | |

| BSM | I | | |
|------------------------|---------------------------|--------------------|-------------------------|
| BSM-0378 | Heat | | |
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.19 | C | | |
| 1.22 | Μ'n | | |
| 0.014 | ס | | |
| 1.22 0.014 0.008 0.26 | s | | Chemical Analysis (wt%) |
| 0.26 | Si | | Analysis |
| 0.02 | ಧ | | (wt%) |
| 0.02 | CL | | |
| 0.01 | Mo | | |
| 0.01 | N. | | |
| 0.020 | < | | |
| 0.012 | Ti | | |
| 0.031 | Nb | | |
| 0.0001 | В | | |
| 0.41 | (IIW) | Я | |
| 0.42 | (CSA) | Я | |

| | | Т | | Т |
|--------------|--------------------|--------------------|----------------|-----------------------|
| | BSM-0378 | Heat | | |
| | BSM-0378 Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 78 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechan |
| Longitudinal | Transverse | 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 39,800 | 45,900 | psi | Yield (Rt0.5) | |
| 39,000 | 44,500 | psi | Yield (Rp0.2) | |
| 70,500 | 71,000 | psi | Tensile (Rm) | |
| 0.56 | 0.65 | (Rt0.5/Rm) | ٧/٦ | |
| 46 | 45 | % | Elongation (A) | |

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination.

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng. 2012 July 6