

Will Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 **Bri-Steel Manufacturing Inc.**

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0382

Product Size:

NPS 30 STD

Production Date:

June 27, 2012

Production Method: Hot Expansion

Product Heat Treatment:

As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2012 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 30 STD ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0382 (PIPE # LENGTH MASS) 118.61b/ft NDE 630PSI NACE MR0175 2012/06 MADE IN CANADA.

		·			
	BSM-0382	Heat			
	Heat	Test Type			
	30	NPS]]_	
	STD	SCH		Product Details	
	7	Pieces		IS	
	DRL	Length		,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	
	118.60	lb/ft	Mass		
	S	μR/hr	Geiger		
	<20	Gauss	Res.Mag.		
	Pass	Insp.	Visual		
	Pass	OD		Non-D	
	Pass	WT	TU	estructive T	
		ASTM E213 AS	ΤU	esting	
	Pass	ij	LI3		
	Pass	/I E309 630 psi/5s	HydroTest		
	37.5° Bevel	5s Condition	End		

BSM-0382	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.19	C		
0.86	Μ'n		
0.009	P		
0.86 0.009 0.006	S		Chemica
0.23	Si		Chemical Analysis (wt%)
0.04	ਨ		(wt%)
0.11	Cı		
0.01	Мо		
0.03	N:		
0.002	<		
0.001	=1		
0.001	Nb		
0.0002	В		
0.35	(MII)	Ж	
0.36	(ASS)	유	

	BSN			Γ
	1-0382	leat		
	BSM-0382 Heat	Heat Test Type		
	Ferrite & Pearlite	Microstructure		
	76	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test 50mm GL; 38mm x WT	Tension Test	Mechanical Properties
50,500	49,500	psi	Yield (Rt0.5)	
50,500	45,100	psi	Yield (Rp0.2)	
71,500	74,500	psi	Tensile (Rm)	
0.71	0.66	(Rt0.5/Rm)	Τ/Υ	
44	44	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. No weld repairs have been performed on this product. This product has no mercury contamination.

✓ This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1

Mill Test Certificate approved by:

Kenton Dechant, P.Eng.

2012 July 6

Manager of Quality and R&D