

## Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-0393

Mill Test Certificate

Product Size: NPS 20 TRUE80

Production Date: July 4, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B/C, A/SA53-2012 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 20 TRUE80 ASTM/ASME A/SA106 GR B/C A/SA53 GR B HEAT BSM-0393 (PIPE # LENGTH MASS) 208.91b/ft NDE 1000PSI NACE MR0175 2012/07 MADE IN CANADA.

	BSM-0393	Heat		
	Heat	Test Type		
	20	NPS		P
	TRUFSO	SCH		Product Detail
(	ىر	Pieces		ils
0.77	DR!	Length		
100.00	208 90	lb/ft	Mass	
3	25	μR/hr	Geiger	
720	000	Gauss	Res.Mag.	
1 033	Dace	Insp.	Visual	
1 000	Dacc	OD		Non-E
r doo	Dacc	TW	TU	Destructive 1
-		ASTM E213	TU	esting
rass	Dace	ASTM E309	ET	
rass	Dace	1000 psi/5s	HydroTest	
ridili Ellu	ם ביים	Condition	End	

BSM-0393	Heat		
Heat	Test Type		
Refining; Vacuum Degas	Blast Furnace; EAF; Ladle	Steelmaking Method	
0.16	С		
0.99	Mn		
0.015	P		
0.99 0.015 0.004	S		Chemical
0.25	Si		l Analysis (wt%)
0.05	Cr		(wt%)
0.06	CL		
0.01	Mo		
0.02	Z.		
0.004	٧		
0.002	Ti		
0.001	Nb		
0.0001	В		
0.34	(MII)	Э	
0.34	(CSA)	Œ	

	BSM-0393 Heat	Heat		100
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	75	HRBW	Hardness	
	Pass	Flattening Test		Mechan
Longitudinal	Transverse	Flattening Test   50mm GL; 25mm x WT	Tension Test	Mechanical Properties
48,600	63,000	psi	Yield (Rt0.5)	
47,900	61,500	psi	Yield (Rp0.2)	
70,500	71,500	psi	Tensile (Rm)	
0.69	0.88	(Rt0.5/Rm)	Τ/Υ	
54	58	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

 $\checkmark~$  This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

Service, and NACE MR0103-2010 Section 2.1.

No weld repairs have been performed on this product. This product has no mercury contamination

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

2012 Aug 20