

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0407

Product Size:

NPS 24 SCH 60

Production Date: July 9, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASTM/ASME A/SA106-2011 Grade B, A/SA53-2012 Grade B Type S, NACE MR0175-2009

Product Markings: .BRI-STEEL MFG NPS 24 SCH 60 ASTM/ASME A/SA106 GR B A/SA53 GR B HEAT BSM-0407 (PIPE # LENGTH MASS) 238.1lb/ft NDE 1000PSI NACE MR0175 2012/07 MADE IN CANADA.

| | | _ | _ | Т |
|--|-----------|-------------|-----------|----------------|
| | BSM-0407 | Heat | | |
| | Heat | Test Type | | |
| | 24 | NPS | | Ī |
| | SCH 60 | Thickness | Wall | Product Detail |
| | ω | Pieces | | S |
| | DRL | Length | | |
| | 238.10 | lb/ft | Mass | |
| | <5 | μR/hr | Geiger | |
| | <20 | Gauss | Res.Mag. | |
| | Pass | Insp. | Visual | |
| | Pass | OD | | Non-I |
| | Pass | WT | TU | Destructive ' |
| The second secon | | ASTM E213 | TU | Testing |
| | Pass | ASTM E309 | T3 | |
| | Pass | 1000 psi/5s | HydroTest | |
| | Plain End | Condition | End | |

| BSM-0407 | Heat | | |
|------------------------|---------------------------|--------------------|-------------------------|
| Heat | Test Type | | |
| Refining; Vacuum Degas | Blast Furnace; EAF; Ladle | Steelmaking Method | |
| 0.14 | С | | |
| 1.07 | Mn | | |
| 0.017 | Р | | |
| 0.005 | S | | Chemical Analysis (wt%) |
| 0.26 | Si | | l Analysis |
| 0.09 | Cr | | (wt%) |
| 0.07 | Cu | | |
| 0.02 | Mo | | |
| 0.03 | <u>z</u> | | |
| 900.0 | < | | |
| 0.003 | =! | | |
| 0.001 | Nb | | |
| 0.0002 | В | | |
| 0.35 | (IIW) | CE | |
| 0.33 | (CSA) | Œ | |

| | BSM-0407 Heat | Heat | | |
|--------------|--------------------|--------------------------------------|----------------|-----------------------|
| | Heat | Test Type | | |
| | Ferrite & Pearlite | Microstructure | | |
| | 74 | HRBW | Hardness | |
| | Pass | Flattening Test | | Mechan |
| Longitudinal | Transverse | Flattening Test 50mm GL; 38mm x WT | Tension Test | Mechanical Properties |
| 45,600 | 44,900 | psi | Yield (Rt0.5) | |
| 45,200 | 43,000 | psi | Yield (Rp0.2) | |
| 67,500 | 68,500 | psi | Tensile (Rm) | |
| 0.68 | 0.66 | (Rt0.5/Rm) | Τ/Υ | |
| 60 | 57 | % | Elongation (A) | |

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the 🗸 We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. This pipe product meet the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product. This product has no mercury contamination

 $\checkmark~$ This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

2013 Feb 20

Manager of Quality and R&D Kenton Dechant, P.Eng