

## Mill Test Certificate

**Bri-Steel Manufacturing Inc.** 

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0469

Product Size:

NPS 24 STD

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Production Date: September 11, 2012

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B/C A/SA53 GR B NPS 24 STD HEAT BSM-0469 (PIPE # LENGTH MASS) 94.621b/ft NDE 670PSI SMLS NACE MR0175 2012/09 MADE IN CANADA.

BSM-0469	неат	=	
Heat	1		
24	NPS	;	
STD	Ihickness	Wall	Product Detail
12	Pieces	*	ils
DRL	Length		
94.62	lb/ft	Mass	
G	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	insp.	Visual	
Pass	OD		Non-Dest
Pass	WT	TU	tructive
Pass	ASTM E213 AS	T	Testing
Pass	_	ET	
Pass	M E309 670 psi/5s (	HydroTest	
37.5° Bevel	Condition	End	

	BSM-0469		Heat	:		
Vacuum Degas; Fully Killed	ВІа		Steelmaking Method			
Product	Heat		Analysis			
0.22	0.21		0			
0.88	0.85		S			
0.011	0.010		ъ			
0.011 0.013	0.011		S		Chemical Analysis (wt%)	
0.23	0.22		S:		Analysis	
0.05	0.05		<del>ر</del>		(wt%)	
0.07	0.07		U C			
0.02	0.01		M <sub>o</sub>			
0.04	0.05		Z.			
0.002	-		<			
0.001	,					
0.001	t		N <sub>D</sub>			
0.0002	0.0003		В			
0.39	1	11111	3	CE		
0.40	1	10011	(CSA)	Œ		

	BSM-0469 Heat	Heat		
	Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	77	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
46,200	42,900	psi	Yield (Rt0.5)	
46,200	42,500	psi	Yield (Rp0.2)	
72,000	74,000	psi	Tensile (Rm)	
0.64	0.58	(Rt0.5/Rm)	۲/۲	
42	43	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

results meet the corresponding requirements.

Service, and NACE MR0103-2010 Section 2.1. This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product

This certificate represents a quality control system that is compliant with EN 10204;2004 Type 3.1. This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

Mill Test Certificate approved by:

Manager of Quality and R&D Kenton Dechant, P.Eng.

20120 ct 25