

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0487

Product Size:

NPS 24 TRUE80

Production Date:

Production Method: Hot Expansion Product Heat Treatment: As-rolled

October 6, 2012

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 TRUE80 HEAT BSM-0487 (PIPE # LENGTH MASS) 296.41b/ft NDE SMLS NACE MR0175 2012/10 MADE IN CANADA.

	BSM-0487	Heat		
	Heat	Test Type		
	24	NPS		T.
	TRUE80	Thickness	Wall	Product Detail
	12	Pieces		ls
	DRL	Length		
	296.40	lb/ft	Mass	
	5	μR/hr	Geiger	
	<20	Gauss	Res.Mag.	
	Pass	Insp.	Visual	
	Pass*	OD		Non-I
	Pass	WT	듸	Destructive 1
	Pass	ASTM E213	TU	e Testing
	Pass	ASTM E309	ET	
	1		HydroTest	
	Plain End	Condition	End	

Ì	_		_		_
		BSM-0487	Heat		
	Vacuum Degas; Fully Killed	Blast Furnace; EAF; Ladle Refining;	Steelmaking Method		
	Product	Heat	Analysis		
	0.20	0.19	C		
	0.92	0.92	Mn		
	0.011 0.014	0.009	ъ		
	0.014	0.012	S		Chemical Analysis (wt%)
	0.25	0.25	<u>S</u> :		Analysis
П	0.09	0.08	cr		(wt%)
	0.07	0.07	U.		
	0.02	0.01	Mo		
	0.03	0.03	Z.		
	0.002	1	<		
	0.001	1	Ti		
	0.001	1	Nb		
	1000.0	0.0004	В		
	0.38	,	(IIW)	E	
0.00	0.39	1	(CSA)	CE	

	BSM-0487 Heat	Heat		
	Heat	Test Type	C 200	
	Ferrite & Pearlite	Microstructure		
	73	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 38.1mm x WT	Transverse; 38.1mm x WT	50mm GL	Tension Test	Mechanical Properties
40,300	47,100	psi	Yield (Rt0.5)	
38,400	48,500	psi	Yield (Rp0.2)	
69,500	70,000	psi	Tensile (Rm)	
0.58	0.67	(Rt0.5/Rm)	Τ/Υ	
54	54	%	Elongation (A)	

Additional Details:

Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

results meet the corresponding requirements.

No weld repairs have been performed on this product. Service, and NACE MR0103-2010 Section 2.1.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

* OD Tolerance as per API 5L

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 2012 oct 10

Manager of Quality and R&D