

Mill Test Certificate

Bri-Steel Manufacturing Inc.

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-0500

Product Size:

NPS 24 SCH 120

Production Date:

October 16, 2012

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2011 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009, MR0103-2010

Product Markings: .BRI-STEEL MFG ASTM/ASME A/SA106 GR B A/SA53 GR B NPS 24 SCH 120 HEAT BSM-0500 (PIPE # LENGTH MASS) 429.4lb/ft NDE SMLS NACE MR0175 2012/10 MADE IN CANADA.

BSM-0500	Heat		
Heat	Test Type		
24	NPS		
SCH 120	Thickness	Wall	Product Detail
6	Pieces		S
DRL	Length		
429.40	lb/ft	Mass	
5	μR/hr	Geiger	
<20	Gauss	Res.Mag.	
Pass	Insp.	Visual	
Pass	OD		Non-E
Pass	WT	TU	estructive
Pass	ASTM E213	TU	Testing
Pass	ASTM E309	ET	
*		HydroTest	
Plain End	Condition	End	

						Chemical Analysis (wt%)	Analysis	(wt%)									
																CE	CE
Heat	Steelmaking Method	Analysis	C	Mn	P	S	Si	Cr	Cu	Mo	N:	<	=	Nb	В	(WII)	(CSA)
RSM-0500	Blast Furnace; EAF; Ladle Refining;	Heat	0.21	0.92	0.015	0.015	0.30	0.04	0.05	0.01	0.02	0.003	0.002	0.001	0.0001	t	к
0000	Vacuum Degas; Fully Killed	Product	0.20	0.92	0.20 0.92 0.015 0.004 0.29 0.04	0.004	0.29		0.05	0.01	0.02	0.004	0.002	0.001	0.0002	0.37	0.38

	BSM-0500	Heat		
	00 Heat	Test Type		
	Ferrite & Pearlite	Microstructure		
	78	HRBW	Hardness	
	Pass	Flattening Test		Mechar
Longitudinal; 19.1mm x WT	Transverse; 19.1mm x WT	50mm GL	Tension Test	Mechanical Properties
38,400	54,500	psi	Yield (Rt0.5)	
37,300	49,900	psi	Yield (Rp0.2)	
68,500	72,500	psi	Tensile (Rm)	
0.56	0.75	(Rt0.5/Rm)	Υ/Τ	
45	40	%	Elongation (A)	

Additional Details:

results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2011, A/SA53-2012 and the purchase order requirements, and that the We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing

Service, and NACE MR0103-2010 Section 2.1. ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour

No weld repairs have been performed on this product.

This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

This certificate represents a quality control system that is compliant with EN 10204;2004 Type 3.1.

* Note that this product was hydrotested to 1000psi.

Mill Test Certificate approved by:

Kenton Dechant, P.Eng. 20120ct23

Manager of Quality and R&D