

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc. Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.brichemsteel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1635 Product Size: 18560

Production Date: Feb 13, 2014

Production Method: **Hot Expansion**

Product Heat Treatment:

As-rolled

Certificate No.: MTR- 000873

Product Standards:

ASME B36.10-2004, API 5L-45th Ed. Grade B PSL1, ASTM/ASME A/SA106-2013 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings

| API > 5L-0898 API SPEC 5L NPS 18 SCH 60 0.750 INCHWT GR B PSL1 SMLS 2014/02 NDE 2000PSI MANULASHUEINGING HEAT BSM-1635 (PIPE # LENGTH MASS) 138.21b/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

BSIVI-1635	100		11000	Host		
неат			i car i ypc	Test Type		
NPS 18 SCH 60 0.750lh. WT	100 10 COLL CO 0 750: 11/1			Product Size	Product: Details	
TO	,		Fieces	Diacas		
DKL	2		rengui			
138.2	,	lb/ft	CCDIVI	2351		
ŝ	,	μR/hr	Colgo	Goiror	20.000	
OT>		Gauss	ives. Mag.	Boc Mag		
Pass		Insp.	Visual	Vicual	85 0	
Pass	,		C	2	No	
Pass	,	٧T	_	111	on-Destruc	
Pass	,	ASTM E213 ASTM	<u>c</u>	-	Non-Destructive Testing	
Pass	,			FT		
Pass	7	2000 PSI/ 5 s	Hydrorest	HydroTest		
Plain End		5 _S Condition	Ē	T 5		

	BSM-1635	Heat	
Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed		Steelmaking Method	
Product	Heat	Test Type	
0.23	0.19	С	
0.89	0.83	Mn	
0.018	0.015	Р	
0.017	0.015 0.012	S	Chemical
0.26	0.25	Si	Chemical Analysis (wt%)
0.07	0.06	Cr	wt%)
0.02	0.01	Си	
0.01		Мо	
0.03	0.03	N:	
0.002		٧	
0.003		Ti	
0.001		Nb	
0.0003		В	
0.39	1	CE(IIW)	
0.39	1	CE(CSA)	

1	_	_		
200	BSM-1635		Heat	
	Heat		Test Type	
	Ferrite & Pearlite		Microstructure	
	71 HRBW		Hardness	
	Pass		Flattening Test	
	Longitudinal; 38.1 mm x WT	50mm GL	Tension Test	Mechanical Properties
The second secon	40,500	psi	Yield (Rt0.5)	
	71,000	psi	Tensile (Rm)	
	0.57	(Rt0.5/Rm)	Υ/Τ	
200 00 00 00 00 00 00 00 00 00 00 00 00	51	%	Elongation (A)	

BSN		
BSM-1635		Heat
į.	Standard	Test
	Sample Details	Impact Test
-	°C	Temp
·	J	
	Ĺ	Impact
ř	_	Energy
ï	AVG	
·	%	
1	%	% Shear
1	%	ear
	AVG	
Ü	mm	
i	mm	Lateral Ex
1	mm	kpansion
1	AVG	

Additional Details:

- \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in and that the results meet the corresponding requirements. accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2013 Grade B/C A/SA53-2012, and the purchase order requirements,
- \checkmark This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Sanden 2014 1-88 19

Assistant QA Manager Paul Sowden, T.T.