

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 www.brichemsteel.com Tel: 001 (780) 469-6603

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1657 Product Size: 16XS

Production Date: Feb 24, 2014

Production Method: Hot Expansion

Product Standards:

As-rolled

Certificate No.: MTR- 000904

ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A/SA106-2013 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010 Product Heat Treatment:

**Product Markings** | API & L\C No. > API SPEC 5L NPS 16 XS 0.500 INCHWT GR B/X42 PSL1 SMLS 2014/02 NDE 2240PSI MASS) 82.77lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

| BSM-1657              |                | Heat         |                         |
|-----------------------|----------------|--------------|-------------------------|
| Heat                  |                | Test Type    |                         |
| NPS 16 XS 0.500in. WT |                | Product Size | Product: Details        |
| 2                     |                | Pieces L     |                         |
| DRL                   |                | Length       |                         |
| 82.77                 | lb/ft          | Mass         |                         |
| <5                    | μR/hr          | Geiger       |                         |
| <10                   | Gauss          | Res. Mag.    |                         |
| Pass                  | Insp.          | Visual       |                         |
| Pass                  |                | OD           | N                       |
| Pass                  | TW             | TU           | on-Destruct             |
| Pass                  | ASTM E213 ASTM | TU           | Non-Destructive Testing |
| Pass                  | ASTM           | ET           |                         |
| Pass                  | 2240 PSI/ 5 s  | HydroTest    |                         |
| 32.5° Bevel           | Condition      | End          |                         |

|   | BSM-1657   | Heat               |                        |
|---|--|--------------------|------------------------|
| C Day of the control | Blast Furnace; EAF; Ladle Refining; Vacuum Degas: Fully Killed | Steelmaking Method |                        |
| Product   | Heat   | Test Type          |                        |
| 0.21  | 0.19   | С                  |                        |
| 0.95  | 0.94   | Mn                 |                        |
| 0.011   | 0.010  | P                  |                        |
| 0.010   | 0.004  | S                  | Chemical               |
| 0.28  | 0.25   | Si                 | Chemical Analysis (wt% |
| 0.03  | 0.03   | Cr                 | wt%)                   |
| 0.07  | 0.07   | Cn                 |                        |
| 0.01  | 0.01   | Mo                 |                        |
| 0.04  | 0.04   | Ni                 |                        |
| 0.002   |  | ٧                  |                        |
| 0.001   |  | Τi                 |                        |
| 0.001   |  | Nb                 |                        |
| 0.0003  | 0.0005   | В                  |                        |
| 0.39  | 1  | CE(IIW)            |                        |
| 0.39  | 1  | CE(CSA)            |                        |

| BSM-:                      |            | Ŧ               |                       |
|----------------------------|------------|-----------------|-----------------------|
| BSM-1657                   |            | Heat            |                       |
| Heat                       |            | Test Type       |                       |
| Ferrite & Pearlite         |            | Microstructure  |                       |
| 77 HRBW                    |            | Hardness        |                       |
| Pass                       |            | Flattening Test |                       |
| Longitudinal; 38.1 mm x WT | 50mm GL    | Tension Test    | Mechanical Properties |
| 44,400                     | psi        | Yield (Rt0.5)   |                       |
| 72,000                     | psi        | Tensile (Rm)    |                       |
| 0.62                       | (Rt0.5/Rm) | Υ/Τ             |                       |
| 41                         | %          | Elongation (A)  |                       |

|     |          |           |    |     |       |      |   |     |        |        |   |      |                |          | The second secon |
|-----|----------|-----------|----|-----|-------|------|---|-----|--------|--------|---|------|----------------|----------|--|
|     | ï        | ı         | 1  | ı   | ı     |      | 1 | •   | ,      | 1      | ı | ,    | t              | 10       | BSM-1657   |
| AVG | mm       | mm        | mm | AVG | %     | %    | % | AVG | J      | J      | _ | ြိ   | Sample Details | Standard |  |
|     | xpansion | Lateral E |    |     | Shear | % Sh |   |     | Energy | Impact |   | Temp | Impact Test    | Test     | Heat   |

## Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2013 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- $\checkmark$  This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- $\checkmark$  No weld repairs have been performed on this product.
- $\checkmark$  This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Boundar 2014 FEB 26

Paul Sowden, T.T.

Assistant QA Manager