

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 124

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603 www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-1729 Product Size: 16S100

Production Date: Mar 26, 2014

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Certificate No.: MTR- 001000

Product Standards: ASME B36.10-2004, ASTM/ASME A/SA106-2013 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings NPS 16 SCH 100 1.031 INCHWT SMLS 2014/03 NDE

PRODUCT MARKINGS NACE MR0175/MR0103 MADE IN CANADA

PRODUCT MARKINGS NACE MR0175/MR0103 MADE IN CANADA

BSM-1/29			Heat	
неат	+		Test Type	
NPS 16 SCH 100 1.031 in. WT			Product Size	Product: Details
щ			Pieces Length	
DRL			Length	
164.8		lb/ft	Mass	
Ġ		uR/hr	Geiger	
410		Gauss	Res. Mag.	
Pass		insp	Visual	
Pass			OD **	Nor
Pass		5	드	Non-Destructive Testi
Pass		ASTM F213	F	tive Testing
Pass		ASTM F213 ASTM F309	ET	
•			HydroTest	
Plain End		Condition	End	

3	BSM-1729 Biss	Heat	
Control of the state of the sta	Blast Furnace; EAF, Ladle Refining: Vacuum Deers: Fully Killed	Steelmaking Method	
Product	Heat	Test Type	
0.20	0.21	C	
0.89	0.90	Mn	
0.015	0.017	P	C
0.002	0.002	S	Chemical Analysis (wt%)
0.31	0.29	Si	Analysis
0.06	0.06	Cr	(wt%)
0.08	0.06	Cu	
0.01	0.01	Mo	
0.03	0.02	N:	
0.003	0.004	٧	
0.001	0.002	Ti	
0.001	0.001	Nb	
0.0003	0.0002	В	
0.37		CE(IIW)	
0.37	,	CE(CSA)	

BSM-1729		Heat	
Heat		Test Type	
Ferrite & Pearlite		Microstructure	
76 HRBW		Hardness	
Pass		Flattening Test	~
Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties
48,800	psi	Yield (Rt0.5)	
68,500	psi	Tensile (Rm)	
0.71	(Rt0.5/Rm)	1/4	
48	%	Elongation (A)	

Additional Details:

- \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing that the results meet the corresponding requirements. Inc. in accordance with ASTM/ASME A/SA106-2013 Grade B A/SA53-2012, and the purchase order requirements, and
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3
 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- Note that this product was hydrotested to 1000 psi for 5 seconds.
- **OD Tolerances as per API

Mill Test Certificate approved by:

Assistant QA Manager Paul Sowden, T.T.