

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc. Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1813 Product Size: 20S140

Production Date:

May 05, 2014

Production Method: **Hot Expansion**

Product Heat Treatment: As-rolled

ASME B36.10-2004, ASTM/ASME A/SA106-2013 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Certificate No.: MTR- 001079

Product Markings

Product Standards:

NPS 20 SCH 140 1.750 INCHWT SMLS 2014/05 NDE HEAT BSM-1813 (PIPE # LENGTH MASS) 341.1lb/ft ASTM/ASME A/SA106 GR B A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

Plain End	*	Pass	Pass	Pass	Pass	Pass	<10	5	341.1	DRL	2	NPS 20 SCH 140 1.750in. WT	Heat	BSM-1813
Condition		ASTM	ASTM E213 ASTM	WT		insp.	Gauss	μR/hr	lb/ft					
End	HydroTest	甲	Ч	UŢ	OD	Visual	Res. Mag.	Geiger	Mass	Length	Pieces	Product Size	Test Type	Heat
			tive Testing	Non-Destructive Testing	Z							Product: Details		

	BSM-1813	Heat	
Degas; rully Nilled	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
Product	Heat	Test Type	
0.20	0.18	С	
0.90	0.90	Mn	
0.90 0.011 0.004	0.90 0.008 0.004	P	
0.004	0.004	S	Chemical Analysis (wt%)
)4 0.31	0.28	Si	Analysis (
0.04	0.04	Cr	wt%)
0.05	0.06	Си	
0.01	0.00	Mo	
0.02	0.02	N:	
0.002	0.001	٧	
0.002	0.002	П	
0.001	0.001	Nb	
0.0003	0.0003	В	
0.37	1	CE(IIW)	
0.37	111	CE(CSA)	

1	-		_	_
The second secon	BSM-1813		Heat	
A 228 48526 433	Heat		Test Type	
	Ferrite & Pearlite		Microstructure	
	77 HRBW		Hardness	
	Pass		Flattening Test	_
	Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties
200 0000	46,100	psi	Yield (Rt0.5)	
The second second second second	68,500	psi	Tensile (Rm)	
The second secon	0.67	(Rt0.5/Rm)	Υ/Τ	
	52	%	Elongation (A)	

							ľ		ı	ı		-		-	BSM-1813
AVG % % AVG mm mm mm	% % % AVG mm	% % % AVG	% % %	AVG % % %	AVG % %	AVG %	AVG		Ĺ	J	L	°C	Sample Details	Standard	
gy % Shear Lateral Expansion	Lateral E	gy %Shear	gy % Shear	gy % Shear	gy %SI	gy	gy	gy	Ener	Impact		Temp	Impact Test	Test	Heat

Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with ASTM/ASME A/SA106-2013 Grade B A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.
- \checkmark This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.
- * Note that this product was hydrotested to 1100 psi for 5 seconds.

Mill Test Certificate approved by:

posanden 2014 MAY 15

Paul Sowden, T.T.

Assistant QA Manager