

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.bri-steel.com

Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1849

Product Size: 24T80

Production Date: May 20, 2014

Production Method: Hot Expansion

Product Heat Treatment: As-rolled

Certificate No.: MTR-

Product Standards: ASME B36.10-2004, API 5L-45th Ed. Grade B PSL1, ASTM/ASME A/SA106-2013 Grade B NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings

BRI-STEEL | <API & L/C No.> API SPEC 5L NPS 24 TRUE 80 1.219 INCHWT GR B PSL1 SMLS 2014/05 NDE 2160PSI HEAT BSM-1849 (PIPE # LENGTH MASS) 296.4Ib/ft ASTM/ASME A/SA106 GR B A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

070000000000000000000000000000000000000	BSM-1849		Heat	
	9 Heat		Test Type	
	NPS 24 TRUE 80 1.219in. WT		Product Size	Product: Details
	2		Pieces	
	DRL		Length	
	296.4	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<10	Gauss	Res. Mag.	
	Pass	Insp.	Visual	
	Pass		OD	N
	Pass	TW	TU	on-Destruc
	Pass	ASTM E213 ASTM	TU	Non-Destructive Testing
	Pass	ASTM	ET	
	Pass	2160 PSI/ 5 s	HydroTest	
	Plain End	s Condition	End	

		BSM-1849	Heat		
	Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed		Steelmaking Method	(C) (S) (A) (A) (B) (B) (A) (B) (B) (B) (B) (B) (B) (B) (B) (B) (B	
	Product	Heat	Test Type		
	0.19	0.19	С		
	0.85	0.82	Mn		
	0.010	0.82 0.008 0.008	Р		
	0.85 0.010 0.009	0.008	S	Chemical	
	0.23	0.21	Si	Chemical Analysis (wt%)	
	0.05	0.05	Cr	wt%)	
	0.06	0.06	Си		
2000	0.02	0.02	Mo		
	0.02	0.03	N.		
	0.002		٧		
	0.001		Π		
	0.0		Nb		
	0.0002	0.0002	В		
	0.35		CE(IIW)		
	0.35	ı	CE(CSA)		

BSM-1849		Heat		
Heat		Test Type		
Ferrite & Pearlite		Microstructure		
74 HRBW		Hardness	100000000000000000000000000000000000000	
Pass		Flattening Test		
Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties	
39,100	psi	Yield (Rt0.5)		
67,500	psi	Tensile (Rm)		
0.58	(Rt0.5/Rm)	۲/۲		
42	%	Elongation (A)		

	BSM-1849		Heat	
	1	Standard	Test	
	1	Sample Details	Impact Test	
	,	റ്	Temp	
	,	_		
	1	٦	Impact	
	ī	J	Energy	
	1	AVG		
		%		
	•	%	% Shear	
		%	lear	
		AVG		
	ı	mm		
	r	mm	Lateral Expansion	
	1	mm	pansion	
		AVG		

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2013 Grade B A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements.

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1

✓ No weld repairs have been performed on this product.

✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Tonya Lam, C.E.T.

Assistant QA Manager