

Mill Test Certificate

Bri-Steel Manufacturing Inc. 2125-64 Avenue, Edmonton, AB Canada T6P 1Z4

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number:

BSM-1987

Product Size: 18STD

Production Date: Aug 20, 2014

Production Method: Hot Expansion

Product Standards:

Product Heat Treatment:

As-rolled

Certificate No.: MTR- 001302

ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A/SA106-2013 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings | API & L/C No. > API SPEC 5L NPS 18 STD 0.375 INCHWT GR B/X42 PSL1 SMLS 2014/08 NDE 1490PSI MANUFACTURING HEAT BSM-1987 (PIPE # LENGTH MASS) 70.59lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

| BSM-1987 | | Heat | |
|------------------------|----------------|--------------|-------------------------|
| Heat | | Test Type | |
| NPS 18 STD 0.375in. WT | | Product Size | Product: Details |
| 8 | | Pieces | |
| DRL | | Length | |
| 70.59 | lb/ft | Mass | |
| -5 | μR/hr | Geiger | |
| <10 | Gauss | Res. Mag. | |
| Pass | Insp. | Visual | |
| Pass | | 00 | Z |
| Pass | WT | TU | Non-Destructive Testing |
| Pass | ASTM E213 ASTM | TU | tive Testing |
| Pass | ASTM | ET | |
| Pass | 1490 PSI/ 5 s | HydroTest | |
| 32.5° Bevel | s Condition | End | |

| | | BS | Γ | |
|-------------------|---|----------|--------------------|-------------------------|
| | | BSM-1987 | Heat | |
| | Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed | | Steelmaking Method | |
| | Product | Heat | Test Type | |
| | 0.22 | 0.21 | С | |
| | 0.88 | 0.88 | Mn | |
| | 0.021 | 0.012 | Р | |
| | 0.004 | 0.004 | S | Chemical Analysis (wt%) |
| | 0.21 | 0.21 | Si | Analysis (ı |
| 30 | 0.06 | 0.02 | Cr | wt%) |
| | 0.02 | 0.02 | Cu | |
| The second second | 0.01 | 0.01 | Mo | |
| | 0.01 | 0.01 | Ni | |
| | 0.003 | 0.003 | ٧ | |
| | 0.016 | 0.020 | Ti | |
| | 0.001 | | Nb | |
| | 0.0004 | 0.0005 | В | |
| | 0.38 | - | CE(IIW) | |
| | 0.38 | • | CE(CSA) | |

| 8 | | | | |
|---|----------------------------|------------|-----------------|-----------------------|
| | BSM-1987 | | Heat | |
| | Heat | | Test Type | |
| | Ferrite & Pearlite | | Microstructure | |
| | 77 HRBW | | Hardness | |
| | Pass | | Flattening Test | |
| | Longitudinal; 38.1 mm x WT | 50mm GL | Tension Test | Mechanical Properties |
| | 48,000 | psi | Yield (Rt0.5) | |
| | 70,500 | psi | Tensile (Rm) | |
| | 0.68 | (Rt0.5/Rm) | Τ/Υ | |
| | 39 | % | Elongation (A) | |

| | BSM-198 | | Heat | |
|--|----------|----------------|-------------|--|
| | 187 | | # | |
| | 10 | Standard | Test | |
| Company of the Compan | - | Sample Details | Impact Test | |
| | 4 | °C | Temp | |
| | - | J | | |
| natur. | 1 | J | Impact | |
| THE RESERVE STATES AND ADDRESS. | I | J | Energy | |
| | - | AVG | | |
| 103 | 1 | % | | |
| | 1 | % | % Shear | |
| The second second | | % | lear | |
| | - | AVG | | |
| | • | mm | | |
| | - | mm | Lateral Ex | |
| | - | mm | Expansion | |
| | ŧ | AVG | | |

Additional Details:

- \checkmark We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in and that the results meet the corresponding requirements. accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2013 Grade B/C A/SA53-2012, and the purchase order requirements,
- \checkmark This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Anh. 22.2014

Tonya Lam, C.E.T.

Assistant QA Manager