

Product:

Seamless Carbon Steel Pipe

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.bri-steel.com

Product Heat Number: BSM-2050 Product Size: 24S60 Production Date: Sep 30, 2014

Production Method: **Hot Expansion** Product Heat Treatment: As-rolled Certificate No.: MTR- 001384

Product Standards: ASME B36.10-2004, API 5L-45th Ed. Grade B PSL1, ASTM/ASME A/SA106-2014 Grade B/C NDE, A/SA53-2012 Grade B Type S, NACE MR0175-2009 MR0103-2010

Product Markings HEAT BSM-2050 (PIPE # LENGTH MASS) 238.1lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA <API & L/C No.> API SPEC 5L NPS 24 SCH 60 0.969 INCHWT GR B PSL1 SMLS 2014/09 NDE 1900PSI

BSM			
BSM-2050		Heat	
Heat		Test Type	
NPS 24 SCH 60 0.969in. WT		Product Size	Product: Details
1		Pieces	
DRL		Length	
238.1	lb/ft	Mass	
< 5	μR/hr	Geiger	Ann.
<10	Gauss	Res. Mag.	0.00
Pass	Insp.	Visual	
Pass		OD	No
Pass	TW	ΤU	Non-Destructive Testing
Pass	ASTM E213 ASTM	TU	tive Testing
Pass	ASTM	ET	
Pass	1900 PSI/ 5 s Condition	HydroTest	
Plain End	S Condition	End	

	_		_	_
			Heat	
	cegas, runy sines	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
	Product	Heat	Test Type	
	0.18	0.20	С	
	0.97	0.90	Mn	
	0.010	0.011	Р	
2	0.003	0.019	S	Chemical Analysis (wt%)
	0.27	0.27	Si	Analysis (
	0.06	0.05	Cr	wt%)
	0.07	0.06	Cu	
	0.01	0.01	Мо	
	0.03	0.03	N:	
	0.003	0.003	٧	
	0.001	0.002	Π	
	0.000	0.001	Nb	
	0.0004	0.0003	В	
	0.36	-	CE(IIW)	
	0.36	1	CE(CSA)	
		Product 0.18 0.97 0.010 0.003 0.27 0.06 0.07 0.01 0.03 0.003 0.001	0.90 0.011 0.019 0.27 0.05 0.06 0.01 0.03 0.003 0.001 0.0001 0.0003 - 0.97 0.010 0.003 0.27 0.06 0.07 0.01 0.03 0.001 0.000 0.0004 0.36	Steelmaking Method Test Type C Mn P S Si Cr Cu Mo Ni V Ti Nb B CE(IIW) Blast Furnace: EAF; Ladle Refining: Vacuum Degas; Fully Killed Heat 0.20 0.90 0.011 0.019 0.27 0.05 0.06 0.01 0.03 0.003 0.001 0.0003 - Degas; Fully Killed Product 0.18 0.97 0.010 0.003 0.07 0.01 0.03 0.001 0.000 0.0004 0.36

BSM-2050		Heat	
Heat		Test Type	
Ferrite & Pearlite		Microstructure	
80 HRBW		Hardness	770,000,000
Pass		Flattening Test	WATER CONTROL OF
Longitudinal; 19.05 mm x WT	50mm GL	Tension Test	Mechanical Properties
50,500	psi	Yield (Rt0.5)	
71,500	psi	Tensile (Rm)	
0.71	(Rt0.5/Rm)	٧/٢	
48	%	Elongation (A)	

		1	,	1	,	,	. :		-		,	,		ı	BSM-2050
	mm	mm	mm	AVG	%	%	%	AVG	ſ	Ĺ	J	°C	Sample Details	Standard	
_	Expansion	Lateral E			hear	% Shear			Energy	Impact		Temp	Impact Test	Test	Heat

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A/SA106-2014 Grade B/C A/SA53-2012, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 and API Q1.

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2010 Section 2.1

✓ No weld repairs have been performed on this product.

✓ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Oct 102/2014

Tonya Lam, C.E.T.

Assistant QA Manager