

Product:

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Fax: 001 (780) 469-6986 Tel: 001 (780) 469-6603

www.bri-steel.com

Production Method: Seamless Carbon Steel Pipe Hot Expansion Product Heat Number: Product Heat Treatment: BSM-2130 As-rolled Product Size: 24STD Certificate No.: MTR- 001460 Production Date: Nov 18, 2014

Product Standards: ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A106-2014/SA106-2013 Grade B/C NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-

Product Markings

HEAT BSM-2130 (PIPE # LENGTH MASS) 94.62lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA <API & L/C No.> API SPEC 5L NPS 24 STD 0.375 INCHWT GR B/X42 PSL1 SMLS 2014/11 NDE 1190PSI

BSM-2130		Heat	
Heat		Test Type	•
NPS 24 STD 0.375in. WT		Product Size	Product: Details
10		Pieces	
DRL		Length	
94.62	lb/ft	Mass	
< 5	μR/hr	Geiger	
<10	Gauss	Res. Mag.	
Pass	Insp.	Visual	
Pass		OD	N
Pass	WT	듸	on-Destruct
Pass	ASTM E213	UT	Non-Destructive Testing
Pass	ASTM	ET	
Pass	1190PSI/ 5 s	HydroTest	
32.5° Bevel	S Condition	End	

	BSN		
	1-2130	Heat	
orgas, rully sincu	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
Product	Heat	Test Type	
0.21	0.20	С	
0.99	0.97	Mn	
0.009	0.010	Р	
0.001	0.008	S	Chemical
0.23	0.20	Si	Chemical Analysis (wt%)
80.0	0.09	Cr	wt%)
0.05	0.04	Cu	
0.01	0.00	Mo	
20.0	0.02	Z.	
200.0	100.0	٧	
0.003		11	
0.001		dN	
0.0004		В	
0.40	ı	CE(IIW)	
0.40	1	CE(CSA)	
	Product 0.21 0.99 0.009 0.001 0.23 0.08 0.05 0.01 0.05 0.003 0.003 0.001 0.0004 0.40	Heat 0.20 0.97 0.010 0.008 0.20 0.09 0.04 0.00 0.02 0.001 0.001 - - Product 0.21 0.99 0.001 0.23 0.08 0.05 0.01 0.05 0.003 0.003 0.001 0.0004 0.40	Steelmaking Method Test Type C Mn P S Si Cr Cu Mo Ni V Ti Nb B CE(IIW) C Blast Furnace; EAF; Ladle Refining; Vacuum Heat 0.20 0.97 0.010 0.008 0.20 0.09 0.09 0.04 0.00 0.02 0.001

-		_	_
BSM-2130		Heat	
Heat		Test Type	
Ferrite & Pearlite		Microstructure	
79 HRBW		Hardness	
Pass		Flattening Test	
Longitudinal; 38.1 mm x WT	50mm GL	Tension Test	Mechanical Properties
47,100	psi	Yield (Rt0.5)	
73,000	psi	Tensile (Rm)	
0.65	(Rt0.5/Rm)	7/ү	
40	%	Elongation (A)	

BSM-2130		Heat	
1	Standard	Test	
3	Sample Details	Impact Test	
,	റ്	Temp	
1	J		
ı	J	Impact	
,	J	: Energy	
ì	AVG		
-	%		
	%	% Shear	
·	%		
1	AVG		
ı	mm		
1	mm	Lateral Expansion	
-	mm		
r	AVG		

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A106-2014/SA106-2013 Grade B/C A53-2012/SA53-2013, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 and API Q1.

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2012 Section 2.1

✓ No weld repairs have been performed on this product.

 \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

NOV/20/2014

Tonya Lam, C.E.T.

Assistant QA Manager