

Product:

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

Seamless Carbon Steel Pipe Product Heat Number: BSM-2283 Product Size: 24STD Production Date: Mar 05, 2015

Production Method: Product Standards: ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A106-2014/SA106-2013 Grade B/C NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-**Hot Expansion Product Heat Treatment:** As-rolled Certificate No.: MTR-

Product Markings

<API & L/C No.> API SPEC 5L NPS 24 STD 0.375 INCHWT GR B/X42 PSL1 SMLS 2015/03 NDE 1180PSI HEAT BSM-2283 (PIPE # LENGTH MASS) 94.62lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

	BSM-2283		Heat	
	Heat		Test Type	
	NPS 24 STD 0.375in. WT		Product Size	Product: Details
	1		Pieces	
	DRL		Length	
	94.62	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<15	Gauss	Res. Mag.	
	Pass	Insp.	Visual	
	Pass		DO	N
	Pass	TW	TU	Non-Destructive Testing
000	Pass	ASTM E213 ASTM	TU	tive Testing
	Pass	ASTM	ΕT	
	Pass	1180PSI/ 5	HydroTest	
	32.5° Bevel	5 _S Condition	End	

ì		В	П	Г
		BSM-2283	Heat	
	regas, rany nineu	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
	Product	Heat	Test Type	
	0.21	0.19	С	
	0.97	0.97	Mn	
	0.009	0.010	Р	
	0.007	0.007	S	Chemical
	0.20	0.20	Si	Chemical Analysis (wt%)
	80.0	0.09	Cr	vt%)
	0.03	Cu 0.04		
	0.01	0.01	Mo	
	0.02	0.02	Z.	
	0.004	0.001	٧	
	0.002	1	Ti	
	0.000	-	Nb	
	0.0006	ı	В	
	0.39	-	CE(IIW)	
	0.39	ı	CE(CSA)	

_		1	<u></u>	_		_
Heat			BSM-2283		Heat	
Standar	Test		Heat		Test Type	
ırd			Ferrite & Pearlite		Microstructure	
Impact Test Sample Details			78 HRBW		Hardness	
റ	Temp		Pass		Flattening Test	
_	Impact Energy		Lon			Mechanic
٦			Longitudinal; 38.1 mm	50m	Tensic	Mechanical Properties
ے	ergy		38.1 m	50mm GL	Tension Test	es
AVG			m x WT			
%	% Shear				Υ:	
%			45,700	psi	Yield (Rt0.5)	
%		1000	7		Ten	
AVG			74,000	psi	Гensile (Rm)	
mm	Lateral I		0.62	(Rt0.5/Rm)	1/7	
mm			32	/Rm)	1	
mm	Lateral Expansion		40	%	Elongation (A)	
AVG			ن	31	ion (A)	

AVG

%

%

%

AVG

mm

mm

mm

AVG

Additional Details:

BSM-2283

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with API 5L-45th Ed., ASTM/ASME A106-2014/SA106-2013 Grade B/C A53-2012/SA53-2013, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 and API Q1.
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2012 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Tonya Lam, C.E.T.

Assistant QA Manager