

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

Product: Seamless Carbon Steel Pipe

Product Heat Number: BSM-2293

Product Size: 18STD

Production Date: Mar 11, 2015

Certificate No.: MTR- 001641

Product Standards: Production Method: ASME B36.10-2004, API 5L-45th Ed. Grade B/X42 PSL1, ASTM/ASME A106-2014/SA106-2013 Grade B/C NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-Hot Expansion Product Heat Treatment: As-rolled

Product Markings

HEAT BSM-2293 (PIPE # LENGTH MASS) 70.59lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA <API & L/C No.> API SPEC 5L NPS 18 STD 0.375 INCHWT GR B/X42 PSL1 SMLS 2015/03 NDE 1490PSI

1	-	_	_	_
	BSM-2293		Heat	
	Heat		Test Type	
	NPS 18 STD 0.375in. WT		Product Size	Product: Details
	10		Pieces	
	DRL		Length	
	70.59	lb/ft	Mass	
	<5	μR/hr	Geiger	
	<10	Gauss	Res. Mag.	
	Pass	Insp.	Visual	
	Pass		OD	No
	Pass	TW	TU	Non-Destructive Testing
	Pass	ASTM E213 ASTM	TU	tive Testing
	Pass	ASTM	ET	
	Pass	1490 PSI/ 5 s	HydroTest	
	32° Bevel	Condition	End	

	BSM-2293	Heat	
ocgos, runy nineu	Blast Furn	Steelmaking Method	
Product	Heat	Test Type	
0.22	0.20	С	
0.90	0.86	Mn	
0.023	0.020	Р	
0.016	0.015	S	Chemical Analysis (wt%)
0.28	0.27	Si	Analysis (
0.06	0.06	Cr	wt%)
0.01	0.01	Cu	
0.01	0.01	Mo	
0.03	0.03	Ni	
0.003	0.002	٧	
0.002	-	Ti	
0.001	-	Νb	
0.0003	ı	В	
0.39	3	CE(IIW)	
0.39	1	CE(CSA)	

BSM-2293		Heat		BSM-2293		Heat			
	Sta	Test Standard		Heat		Test Type			
•	ndard			Ferrit		A10507.5			
Sa		Sa		Ferrite & Pearlite		Microstructure			
	Sample Details	Impact Test ample Details	npact Test	80 HRBW		Hardness			
	Temp			Pass		Flattening Test			
	_			1			Mechar		
t	_	Impact Energy		Longitudinal; 38.1 mm x WT	50	Ten	Mechanical Properties		
1	L		Energy		ıl; 38.1 m	50mm GL	Tension Test	rties	
ı	AVG			m x WT					
t	%					Yie			
ı	%	% Shear	% Sh	% Sh		46,000	psi	Yield (Rt0.5)	
t	%			73		Tens			
ı	AVG			73,500	psi	Tensile (Rm)			
	mm	Lateral Expansion		0.63	(Rt0.5/Rm	I/A			
1	mm		Lateral E	Lateral E		3	/Rm)	_	
1	mm			42	%	Elongation (A)			
1	AVG			2		ion (A)			

Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing Inc. in accordance with results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 and API Q1 API 5L-45th Ed., ASTM/ASME A106-2014/SA106-2013 Grade B/C A53-2012/SA53-2013, and the purchase order requirements, and that the
- √ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2012 Section 2.1
- ✓ No weld repairs have been performed on this product.
- \checkmark This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.
- \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Tonya Lam, C.E.T.

Assistant QA Manager