

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

BSM-2388 Product Size: 30XS Production Date: May 11, 2015

Product Heat Treatment: As-rolled Certificate No.: MTR- 001775

ASME B36.10-2004, ASTM/ASME A/SA333-2013 Grade 6 LT(M45C) A106-2014/SA106-2013 Grade B/C NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-

**Product Markings** 

**Product Standards:** Production Method: Product:

Seamless Carbon Steel Pipe

Product Heat Number:

Hot Expansion

NPS 30 XS 0.500 INCHWT 157.5LB/FT SMLS 2015/05 NDE 800PSI

HEAT BSM-2388 (PIPE # LENGTH MASS) 157.5Ib/ft ASTM/ASME A/SA333 GR 6 LT(M45C) A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

			-	
BSM-2388		Heat		
Heat		Test Type	Product: Details	
NPS 30 XS 0.500in. WT		Product Size		
4		Pieces		
DRL		Length		
157.5	lb/ft	Mass		
<5	μR/hr	Geiger		
<10	Gauss	Res. Mag.		
Pass	insp.	Visual		
Pass		OD	Z	
Pass	WT	TU	Non-Destructive Testing	
Pass	ASTM E213	TU	ive Testing	
Pass	ASTM E309	ΤЭ		
Pass	800 PSI/ 5	HydroTest		
32.5° Bevel	s Condition	End		
	Heat         NPS 30 XS 0.500in. WT         4         DRL         157.5         <5         <10         Pass         Pass         Pass         Pass         Pass	Heat   NPS 30 XS 0.500in. WT   4   DRL   157.5   <5   <10   Pass   Pa	Test Type Product Size Pieces Length Mass Geiger Res. Mag. Visual OD UT UT ET HydroTest length lb/ft lpR/hr Gauss Insp. WT ASTM E213 ASTM E309 800 PSI/ 5  Heat NPS 30 XS 0.500in. WT 4 DRL 157.5 <5 <10 Pass Pass Pass Pass Pass Pass	

Clieffical Allalysis (wt/o)

П

			BSM-2388	Heat
		Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed		Steelmaking Method
The second second second second		Product	Heat	Test Type
	1	0.16	0.18	С
	1	1.24	1.30	Mn
	ı	0.014	0.015	P
	,	0.006	0.008	S
	Ť	0.32	0.32	Si
	ì	0.05	0.05	Cr
	1	0.01	0.01	Cu
	-	0.01	0.01	Mo
	1	0.04	0.04	N:
	1	0.068	0.070	<
	1	0.002	0.001	Ti
	-	0.001	0.001	Nb
	1	0.0005	0.0007	В
	ı	0.40		CE(IIW)
	•	0.40		CE(CSA)

Mechanical Properties

		BSM-2388		Heat
		Heat		Test Type
		Ferrite & Pearlite		Microstructure
		79 HRBW		Hardness
848.838	Pass	Pass		Flattening Test
	Longitudinal; 1.5 in. x WT	Longitudinal; 1.5 in. x WT	2 in. GL	Tension Test
	47,400	47,500	psi	Yield (Rt0.5)
	72,500	72,000	psi	Tensile (Rm)
	0.65	0.66	(Rt0.5/Rm)	Т/А
	46	46	%	Elongation (A)

В	Г		
BSM-2388		Heat	
ASTM A333	Standard ASTM A333		
CVN Long 10 x 10 mm	Sample Details	Impact Test	
-45	ငိ	Temp	
98.5	_		
78.0	_	Impact Energ	
110.5	J	Energy	
95.7	AVG		
20	%		
15	%	% Shear	
30	%	ear	
22	AVG		
1.58	mm		
1.21	mm	Lateral Expansion	
1.88	mm	xpansion	
1.56	AVG		

## Additional Details:

- ✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing in accordance with ASTM/ASME A/SA333-2013 Grade 6 LT(M45C) A106-2014/SA106-2013 Grade B/C A53-2012/SA53-2013, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008
- ✓ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2012 Section 2.1
- No weld repairs have been performed on this product.
- $\checkmark$  This product has not come into contact with mercury during the Bri-Steel Manufacturing processes
- $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Jam May 120/2015

Tonya Lam, C.E.T.

Assistant QA Manager