

Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing Inc.

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986 www.bri-steel.com

Production Method: Product: Seamless Carbon Steel Pipe Hot Expansion

BSM-2403

Product Heat Number:

Product Size: 16T80

Production Date: May 25, 2015

Certificate No.: MTR- 001789

Product Standards: Product Heat Treatment: As-rolled

ASME B36.10-2004, API 5L-45th Ed. Grade B PSL1, ASTM/ASME A106-2014/SA106-2013 Grade B/C NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-2012

Product Markings

<API & L/C No.> API SPEC 5L NPS 16 TRUE 80 0.844 INCHWT 136.5LB/FT GR B PSL1 SMLS 2015/05 NDE 2500PSI HEAT BSM-2403 (PIPE # LENGTH MASS) 136.5lb/ft ASTM/ASME A/SA106 GR B/C A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

	BSM-2403		Heat		
	Heat		Test Type		
	NPS 16 TRUE 80 0.844in. WT		Product Size	Product: Details	
	4		Pieces		
	DRL		Length		
Chemical Analysis (w+%)	136.5	lb/ft	Mass		
8	~ 5	μR/hr	Geiger		
	<20	Gauss	Res. Mag.		
	Pass	insp.	Visual		
	Pass		OD	z	
	Pass	TW	TU	on-Destruc	
	Pass	ASTM E213	TU	Non-Destructive Testing	
	Pass	ASTM E309	ΤЭ		
	Pass	ASTM E213 ASTM E309 2500 PSI/ 5 s Conditio	HydroTest		
		5 s	st		
	Plain End	Condition	End		

m	_		1		_	_	_
BSM-2403		Heat			BSM-2403		Heat
Heat		Test Type			Blast Furnace; EAF; Ladle Refining; Vacuum Degas; Fully Killed		Steelmaking Method
Ferrite & Pearlite		Microstructure					
761		Har			Product 0.22 0.87 0.019 0.012 0.24	Heat	Test Type
76 HRBW		Hardness		-	0.22	0.19	С
Pass		Flattening Test			0.87	0.87	Mn
					0.019	0.010 0.010	Р
Lon	2 in. GL	Tension Test	Mechani	-	0.012	0.010	S
Longitudinal; 0.5 in. Round Bar			Mechanical Properties	1	0.24	0.24	Si
				-	0.07	0.05	Cr
				-	0.01	0.01	Си
41,900		Yield (Rt0.5)		ı	0.01	-	Mo
	psi			-	0.05	0.04	N.
71,000	psi	Tensile (Rm)		1	0.002	-	<
				-	0.002 0.002 0.001	1	Ti
0.59	(Rt0.5/Rm)	1/4		-	0.001		Nb
				-	8000.0	-	В
38	%	Elongation (A)			0.0003 0.39		CE(IIW)
		on (A)		t	0.39	ar.	CE(IIW) CE(CSA)

Longitudinal; 0.5 in. Round Bar

BSM-2403		Heat	
ı	Standard	Test	
1	Sample Details	Impact Test	
0	റ്	Temp	
	J		
	۲.	Impact E	
1	J	: Energy	
•	AVG		
1	%		
1	%	% Shear	
	%	near	
1	AVG		
	mm		
,	mm	Lateral Ex	
,	mm	l Expansion	
1	AVG		

Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing in accordance with API 5L-45th Ed., ASTM/ASME A106-2014/SA106-2013 Grade B/C A53-2012/SA53-2013, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 and API Q1.

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service-2009 NACE MR0103-2012 Section 2.1

✓ No weld repairs have been performed on this product.

√ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes.

 \checkmark This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Mill Test Certificate approved by:

Tonya Lam, C.E.T.

Assistant QA Manager