

## Mill Test Certificate

2125-64 Avenue, Edmonton, AB Canada T6P 1Z4 Bri-Steel Manufacturing

Tel: 001 (780) 469-6603

Fax: 001 (780) 469-6986

www.bri-steel.com

Product Heat Number: BSM-2753 Product Size: NPS 16 XS Production Date: May 04, 2016

Certificate No.: MTR- 002814

ASME B36.10M-2015, ASTM/ASME A333-2015/SA333-2013 Grade 6 LT(M45C) A106-2014/SA106-2013 Grade B NDE, A53-2012/SA53-2013 Grade B Type S, NACE MR0175-2009 MR0103-2012

Product Heat Treatment:

As Rolled

NPS 16 XS 0.500 INCHWT SMLS 2016/05 NDE 1310PSI

**Product Markings** 

Product Standards: Production Method:

Product:

Seamless Carbon Steel Pipe

**Hot Expansion** 

HEAT BSM-2753 (PIPE # LENGTH MASS) 82.77lb/ft ASTM/ASME A/SA333 GR 6 LT(M45C) A/SA106 GR B A/SA53 GR B NACE MR0175/MR0103 MADE IN CANADA

BS	Π		Π
M-2753		Heat	
Heat		Test Type	
NPS 16 XS 0.500in. WT		Product Size	Product: Details
6		Pieces	
DRL		Length	
82.77	lb/ft	Mass	
<5	μR/hr	Geiger	
<20	Gauss	Res. Mag.	
Pass	Insp.	Visual	
Pass		OD	N
Pass	WT	TU	on-Destruc
N12.5 Pass	ASTM E213	TU	Non-Destructive Testing
-	ASTM E309	LЭ	
Pass	1310PSI/ 5.	HydroTest	
31° Bevel	s Condition	End	
	NPS 16 XS 0.500in. WT 6 DRL 82.77 <5 <20 Pass Pass Pass N12.5 Pass - Pass	Heat NPS 16 XS 0.500in. WT 6 DRL 82.77 <5 <20 Pass Pass Pass N12.5 Pass - Pass Pass -	Test Type Product Size Pieces Length Mass Geiger Res. Mag. Visual OD UT UT ET HydroTest Insp. WT ASTM E213 ASTM E309 1310 PSI/ 5 s  Heat NPS 16 XS 0.500in. WT 6 DRL 82.77 <5 <20 Pass Pass Pass N12.5 Pass - Pass

		3SM-2753	Heat	
	ocgas, i any milea	Blast Furnace; EAF; Ladle Refining; Vacuum	Steelmaking Method	
	Product	Heat	Test Type	
ı		0.17	0	
1	1.23	1.18	Mn	
	0.012	0.016	Р	
ı	0.004	0.002	S	
1	0.17 1.23 0.012 0.004 0.29	0.25	Si	
1	0.05	0.17 1.18 0.016 0.002 0.25 0.05	Cr	, , , , , , , , , , , , , , , , , , , ,
ı	0.02	0.02	Cu	,
1	0.01	0.01	Мо	
-	0.01	0.01	N:	
-	0.052	0.046	٧	
ı	0.002	1	Ti	
t	0.001	-	Nb	
ı	0.0004	1	В	
-	0.40	0.39	CE(IIW)	
ı	1	-	CE(IIW)Max	
T	0.40	0.39	CE(CSA)	

BS

Mechanical Properties

	BSM-2753		Heat
	Heat		Test Type
	Ferrite & Pearlite		Microstructure
	81 HRBW		Hardness
Pass	Pass		Flattening Test
Longitudinal; 1.5 in. x WT	Longitudinal; 1.5 in. x WT	2 in. GL	Tension Test
50 500	51 500	psi	Yield (Rt0.5)
76 500	76 000	psi	Tensile (Rm)
0.66	89.0	(Rt0.5/Rm)	1/7
40	41	%	Elongation (A)

Heat	Test	Impact Test	Temp	Impact Energy Min. (J)	Impact Energy (J)	Shear (%)	Lateral Expansion (mm)
	Standard	Sample Details	°C	(3 Tests) AVG	(3 Tests) AVG	(3 Tests) AVG	(3 Tests) AVG
BSM-2753	ASTM A333	CVN Long 10 x 10 mm	-45	(14/14/14) 18	(228/168/150) 182	(80/60/40) 60	(2.26/2.10/2.00) 2.12

## Additional Details:

✓ We hereby certify that this pipe product was manufactured, sampled, tested and inspected by Bri-Steel Manufacturing in accordance with ASTM/ASME A333-2015/SA333-2013, A106-2014/SA106-2013, A53-2012/SA53-2013, and the purchase order requirements, and that the results meet the corresponding requirements. Bri-Steel Manufacturing is registered and certified to ISO-9001:2008 (APIQR-1584), API Q1, and

√ This pipe product meets the sour service requirements of NACE MR0175/ISO 15156-2:2009 Annex A2 for Region 3 Sour Service , and NACE MR0103-2012 Section 2.1

No weld repairs have been performed on this product.

√ This product has not come into contact with mercury during the Bri-Steel Manufacturing processes

 $\checkmark$  This certificate represents a quality control system that is compliant with EN 10204:2004 Type 3.1.

Tonya Lam, P. Tech (Eng.)

Mill Test Certificate approved by:

Assistant QA Manager